



ArmorFlex® 113 Film

▶ At ILC Dover we “create what’s next” by listening to our customers. In response to operators’ input we’ve developed a new addition to the ArmorFlex® family of films – AF 113. The clarity of the product makes this the clear film of choice for flexible enclosures and flexible isolators.

- ▶ Superior visual clarity, ideal for Flexible Enclosures and Flexible Isolators
- ▶ Polyethylene base film provides excellent solvent resistance
- ▶ Permanent antistat provides better than 1×10^{11} Ohms per square surface resistivity
- ▶ 5 year shelf life
- ▶ No incineration off-gassing concerns



ILC DOVER
creating what's next▶

ArmorFlex® 113 Film

ArmorFlex® 113 Solvent Resistance Solvent Contact Recommendations

Chemical	Resistance
Acetone	Excellent
Acetonitrile	Excellent
Anisole	Good
Butyl Acetate	Very Good
Cyclohexane	Fair
Cyclohexane – Ethyl Acetate (50/50)	Good
Dichloromethane	Very Good
Diethylether	Excellent
Dimethylacetamide	Excellent
Dimethylformamide	Excellent
Ethanol	Excellent
Ethyl Acetate	Very Good
HCL (37.4%)	Excellent
n-Heptane	Good
HMDS	Excellent
Isopropanol	Excellent
KOH (50%)	Excellent
Methanol	Excellent
2-Methoxyethanol	Excellent
n-Methylpiperazine	Very Good
n-Methylpyrrolidone	Excellent
Mineral Oil	Very Good
NaOH (50%)	Excellent
Reagent (3A) Alcohol	Excellent
Tetrahydrofuran	Excellent
Toluene	Very Good
Water, Distilled	Excellent

Criteria	
% Change in Physical Properties	Resistance
0 - 10	Excellent
10 - 20	Very Good
20 - 30	Good
> 30	Fair



Mill impeller and screen change out

The superior visibility provided by AF113 lets you see inside the enclosure as if looking through glass.



Processing drums



ILC DOVER
creating what's next»

Providing Flexible Containment Solutions to the
Pharmaceutical Industry since 1997